

Hegrecat® TA101

General Description

Hegrecat TA101 catalyst is a tertiary amine which has a strong influence on promoting the urethane (polyol-isocyanate) reaction in a variety of flexible and rigid foam as well as CASE applications. It is a mixture of 33% triethylene diamine and 67% dipropylene glycol.

Product Property

Multi-purpose amine catalyst; Gelation catalysis; Easy handling.

Applications

Hegrecat TA101 catalyst is used in the manufacture of all types of polyurethane foam.

Typical Physical Property

Appearance	Colorless to Amber Liquid
Viscosity at 25° C	125
Specific Gravity at 25° C [g/cm]	1.03
Flash Point, ° C (PMCC)	110
Water Solubility	Soluble
Calculated OH number [mgKOH/g]	560

Storage and package Information

Hejia Chemical recommends that our catalysts be stored in a dry and cool area under appropriate ventilation conditions. Each container should be closed tightly to avoid contamination with moisture or other negative influences, which could change the products' performance in the end use. 200kgs per steel drum/ 25kgs per plastic drum.

Shelf Life

36 months from the date of production

Disclaimer

The information contained in this TDS is believed to be accurate to the best of Hejia Chemical's knowledge and belief at the time of the TDS publication. The information is intended to be used as a guideline and for informational purpose only. Consequently we do not warrant that the information or the related products are fit for any particular purpose or use by users and it is user's responsibility to test and confirm the fitness of the product.

Hejia shall NOT BE LIABLE, whether contractually or in tort, for damages caused through the use or the reliance on this information and/or the related products.